

FlyGloss FGBC Base Coat

Acrylic Polyurethane Topcoat



Product FlyGloss FGBC Base Coat

Item Class Base Coat / Clear Coat System

FlyGloss FGBC acrylic polyurethane base coat is intended for use with FGCC clear coat to achieve superior gloss and color retention that outshines and outlasts preceding aerospace market technologies. FGBC is available in both solid and special effect colors. With a solid content of over 50 percent, FGBC offers single coat coverage on almost all colors. In addition, this product has a dry to tape time of 2 hours and a recoat window of 72 hours.

Specifications Product is manufactured to meet the performance requirements of the following specifications:

AMS 3095A* - AIMS 04-04-025 - AIMS 04-04-033 - AIMS 04-04-037 - BAMS 565-018 - MEP 10-125 Type I - BAMS 565-018 (*Listed on QPL)

Activator & Additives

Activator	Activating Thinner	Touch-Up Accelerator
925 (Solid Colors)	FG3002 Slower Dry	PS50
930 (Special Effect Colors)	FG3004 Normal Dry	
	FG3009 Faster Dry	

Use of Primers

3Chem recommends use of P1019 (High Solid Epoxy Primer) and P-1069 (Surfacing Primer) with this system. Please contact your local 3Chem representative for a complete list of epoxy primers which may be utilized with this system.

Surface Preparation

Prepare substrate per OEM requirements. Refer to FlyGloss application guide for detailed instructions or contact your local 3Chem representative for assistance.

Mixing Instructions

Base	Finish	Activator	Mix Ratio
FGBC-2XXX	Solid Colors	925	1:1:.25
FGBC-8XXX	Special Effects	930	1:1:.25
FGCC-XXXX	Required Clear Coat	900	1:1

All Colors:

Shake (Base) for 15 minutes to assure no solid settlement remains in can. Add component B activator to component A paint first. Mix ratio for material is 1-part component A paint, 1-part component B activator, up to .25 parts activating thinner.

***All FGBC base coat colors must be top coated with FlyGloss FGCC clear coat to meet specification requirements.

Induction Time

No induction time is required prior to use. Once mixed together, ensure that admixed material is continuously stirred for at least 5 minutes before proceeding.

FlyGloss FGBC Base Coat

Acrylic Polyurethane Topcoat



Spraying Viscosity Solid Colors: 18-22 Seconds with #2 Zahn cup, Special Effect Colors: 17-21 Seconds with #2 Zahn cup

Pot Life 4 Hours @ 21° Celsius, 70° Fahrenheit

Film Thickness 1-1.5 mils DFT (Only one coat required) Wet film thickness should be 2-3 mils total

Application Instructions

Temperature and Humidity	Minimum	Maximum
Temperature Celsius	11°	35°
Temperature Fahrenheit	52°	95°
Humidity	33%	74%

Spray Equipment

Spray Gun Type	Tip/Nozzle Size	Cap Pressure	Pot Pressure
Conventional Air	1.3 - 1.6 mm	45 to 60 psi	10 to 20 psi
HVLP	1.4 - 1.6mm	10 psi Maximum	10 to 20 psi
Electrostatic	1.2 - 1.5mm	45 to 60 psi	10 to 40 psi

Dry Times 1:1:.25

Temperature	Dry to Recoat	Dry to Tape	Dry to Handle	Clearcoat Window	Full Cure
52-65°F (11-18°C)	2.5 Hours	6 Hours	10 Hours	72 Hours	7 Days
66-85°F (19-29°C)	1.5 Hours	3 Hours	6 Hours	72 Hours	7 Days
86-95°F (30-35°C)	1 Hour	2 Hours	4 Hours	72 Hours	7 Days

Oven Force Dry Instructions 1:1:.25

Flash Time	Oven temperature	Dry to Tape	Dry to Handle	Clearcoat Window	Full Cure
30 Minutes	1 hour @ 110° F (43°C)	1.5 Hours	3 Hours	72 Hours	7 Days

Only mix enough material to be applied on initial coat. Always add component B activator to component A paint. Complete kit of material will yield 2.25 US Gallons (8.5 liters). 1-gallon component A paint, 1-gallon component B activator, 1-quart activating thinner.

Apply one even wet coat of material using a uniform spray pattern. Cross coat may be required to achieve 100% coverage in one single coat depending on color. Certain colors may require additional coats.

Application Instructions PS50 Accelerator Touch Up Application - 1:1 plus accelerator
(No activating thinner should be used)

PS50 Required	Dry to Recoat	Pot Life	Dry to Tape	Dry to Handle	Clearcoat Window	Full Cure
1oz/29ml per admixed gallon	15 Minutes	1 Hour	30 Minutes	2.5 Hours	18 Hours	7 Days

Theoretical Coverage 1100-1200 sq. ft / gallon @ 1 mil 27-28 m² / liter @1 mil
*Coverage based on 100% transfer efficiency rate

FlyGloss FGBC Base Coat

Acrylic Polyurethane Topcoat



Dry Film Weight

Per 25 microns: 27-35 g/m²
Per dry mil: .0057-.0082 lbs./ft²

Color

Available in all gloss color ranges
*Special Effects colors include micas and pearlescent

Gloss

Solid colors: 85 minimum @ 60 degrees
Special Effects colors: 30-60 @ 60 degrees
(Gloss 95 minimum once clear coated with FGCC-100)

Volatile Organic Compound 300 – 380 g/l

Shelf Life

24 Months (When stored in climate-controlled environment between 60-80° F)
*Product may be re-certified upon inspection by 3Chem.

Safety Instructions

Always read material safety data sheet (SDS) and product label before utilizing this product. Product SDS is available upon request.

3Chem Corporation Disclaimer

All information, recommendations, statements, and technical data contained herein are not intended to be comprehensive or exhaustive, but instead are based on tests utilizing present knowledge and current laws. The accuracy and completeness of said tests are in no way guaranteed, nor should they be construed as an express or implied warranty. We believe such information, recommendations, statements, and technical data to be reliable and accurate, but we have no control over the quality or the condition of the many factors affecting the use and application of the product. The user shall depend upon its/his/her own information, data and testing to determine whether the product is suitable for the user's intended use and the user assumes all risks and liability resulting from its/his/her use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. All products supplied, and technical advice given is subject to our standard terms and conditions of sale. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

*Brand names mentioned above are either trademarks of or licensed to 3Chem Corporation.