

Sylka Y3 Series

Waterborne Urethane Interior Coating



Product Sylka Y3 Series Waterborne Urethane Interior Coating

Item Class Specialty Coating

Sylka water reducible urethane topcoat is specially formulated for use on aircraft cabin interior surfaces such as polycarbonates, composites, honeycomb, and plastics. It is extremely versatile and may be applied either as a smooth or textured finish. Once cured this product is extremely tough. It is resistant to scratches, certain chemicals and normal passenger wear and tear.

Specifications Product is manufactured to meet the performance requirements of the following specifications:

14 CFR Part 25.853 (a) Appx F Part I - AITM 3.0005 / ABD 0031 (7.4) (Airbus Toxicity) - AVP3-008 - BSS 7239 (Boeing Toxicity)

Surface Preparation Proper surface preparation is essential to promote good adhesion. First clean the substrate and dry using a very fine scotch pad. Make sure to remove all dust and debris using a clean lint free cloth. Once complete, use isopropyl alcohol, acetone, naphtha, or other approved OEM solvent to remove remaining contaminants. Perform water break test to make sure no residues remain on the substrate.

Mixing Instructions

| Base |
|-----------------------|
| Y31-XXXX (Gloss) |
| Y32-XXXX (Semi-Gloss) |
| Y33-XXXX (Flat) |

Shake single component (Base) for 10-15 minutes. Since Sylka is a single component topcoat, no mixing is required. However, if desired this product can be diluted with distilled water up to 10% by volume. It recommended to filter product before pouring into application equipment.

Spraying Viscosity Gloss Colors: 17-19 Seconds with #2 Zahn cup, Semi-Gloss/Flat Colors: 19-22 Seconds with #2 Zahn cup

Film Thickness 1-1.5 MILS DFT (2 Coats @ 1-1.5 DFT) Wet film thickness should be 1.5-2 mils total between 2 coats

Application Instructions

| Temperature and Humidity | Minimum | Maximum |
|--------------------------|---------|---------|
| Temperature Celsius | 11° | 35° |
| Temperature Fahrenheit | 52° | 95° |
| Humidity | 33% | 74% |

Sylka Y3 Series

Waterborne Urethane Interior Coating



Application Instructions

Spray Equipment

| Spray Gun Type | Tip/Nozzle Size | Cap Pressure | Pot Pressure |
|------------------|-----------------|----------------|--------------|
| Conventional Air | 1.3 - 1.6 mm | 40 to 60 psi | 10 to 20 psi |
| HVLP | 1.4 - 1.6mm | 10 psi Maximum | 10 to 20 psi |
| Electrostatic | 1.2 - 1.5mm | 45 to 60 psi | 10 to 40 psi |

Dry Times

| Temperature (Min/Max) | Dust Free | Dry Hard | Full Cure |
|-----------------------|------------|------------|-----------|
| 52-95°F (11-35°C) | 15 Minutes | 45 Minutes | 48 Hours |

Number of Coats:

Spray 1 -2 coats to achieve desired film thickness.

Reduction Instructions:

For smooth finish product may be reduced 10% utilizing distilled water. However, not required.

For textured surface product should be applied "as is" with no reduction. Spray gun must be regulated to achieve desired textured pattern.

Theoretical Coverage 300-350 sq. ft / gallon @ 1 mil 8-9m² / liter @1 mil
*Coverage based on 100% transfer efficiency rate

Color Available in all color ranges

Gloss Gloss colors: 80 minimum @ 60 degrees
Semi-Gloss colors: 17-30 @ 60 degrees
Flat/Matt Colors: Less than 5 @ 60 degrees
*Also available in satin and custom match finishes

Volatile Organic Compound 140 g/l

Shelf Life 12 Months (When stored in climate-controlled environment between 60-80° F)
*Product may be re-certified upon inspection by 3Chem.

Safety Instructions Always read material safety data sheet (SDS) and product label before utilizing this product. Product SDS is available upon request.

3Chem Corporation Disclaimer

All information, recommendations, statements, and technical data contained herein are not intended to be comprehensive or exhaustive, but instead are based on tests utilizing present knowledge and current laws. The accuracy and completeness of said tests are in no way guaranteed, nor should they be construed as an express or implied warranty. We believe such information, recommendations, statements, and technical data to be reliable and accurate, but we have no control over the quality or the condition of the many factors affecting the use and application of the product. The user shall depend upon its/his/her own information, data and testing to determine whether the product is suitable for the user's intended use and the user assumes all risks and liability resulting from its/his/her use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. All products supplied, and technical advice given is subject to our standard terms and conditions of sale. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

*Brand names mentioned above are either trademarks of or licensed to 3Chem Corporation.