

Glair G30 Series

Semi-Gloss & Flat Colors

High Solid Polyurethane Topcoat



Product Glair G30 Series High Solid Polyurethane Topcoat - Semi-Gloss & Flat Colors

Item Class High Solid Polyurethane Topcoat

Glair G30 Series is a high solid polyurethane decorative topcoat formulated to provide superior resistance and an astonishing appearance. With an average 54% solids per gallon; it also offers better coverage than most other polyurethane coatings on the market. This product is also formulated to surpass conventional polyurethanes with superior chemical resistance and flexibility.

Specifications Product is manufactured to meet the performance requirements of the following specifications:

*AMS 3095 - AIMS 04.04.025 - AIMS 04.04.031 - AIMS 04.04.032 - BAMS 565-009
Type I, Class A, Grade B - DHMS C4.04 - MIL-PRF-85285F Ty I-IV, Cl H, Form M, Gr N
- MEP 10-069

*(On QPL Listing) – Please check 3chem.com for complete specification list

Catalyst & Additives Catalyst/Activator Additive

306 (Semi-Gloss/Flat)	PS40 Accelerator
	CRL25 Rolling/Brushing
	CRL28 Rolling/Brushing High Temperatures

Use of Primers 3Chem recommends use of P1019 (AMS 3095 approved primer) with this system. For component MRO applications, P-1090 primer may be used. Please contact your local 3Chem representative for a complete list of epoxy primers which may be utilized with this system.

Surface Preparation Prepare substrate per OEM requirements. Refer to Glair application guide for detailed instructions or contact your local 3Chem representative for assistance.

Mixing Instructions

Base	Catalyst/Activator	Mix Ratio
G32-XXXX (Semi-Gloss)	306	1:1
G33-XXXX (Flat)	306	1:1

Shake (Base) for 15 minutes to assure no solid settlement remains in can. Add component B catalyst to component A paint first. Mix ratio for material is 1-part component A paint, 1-part component B catalyst. No thinner should be added to semi-gloss or flat colors. (Kit yield either 2 gallons or 2 quarts). Must insure mix ratio is exact to obtain desired semi-gloss or flat finish.

Glair G30 Series

Semi-Gloss & Flat Colors

High Solid Polyurethane Topcoat



Induction Time Although no induction time is needed. Once mixed together, ensure that admixed material is continuously stirred for at least 5 minutes before proceeding.

Spraying Viscosity Semi-Gloss/Flat Colors: 18-22 Seconds with #2 Zahn cup

Pot Life 7 Hours @ 21° Celsius, 70° Fahrenheit

Film Thickness 2-3 MILS DFT (2 Coats @ 1-1.5 DFT) Wet film thickness should be 4-6 MILS total between 2 coats

Application Instructions

Temperature and Humidity	Minimum	Maximum
Temperature Celsius	11°	38°
Temperature Fahrenheit	52°	100°
Humidity	33%	74%

Spray Equipment

Spray Gun Type	Tip/Nozzle Size	Cap Pressure	Pot Pressure
Conventional Air	1.3 - 1.6 mm	40 to 60 psi	10 to 20 psi
HVLP	1.4 - 1.6mm	10 psi Maximum	10 to 20 psi
Electrostatic	1.2 - 1.5mm	45 to 60 psi	10 to 40 psi

Dry Times

Temperature	PS40	Wet-Edge	Time Between Coats	Dry to Tape	Dry to Handle	Full Cure
52-65°F (11-18°C)	0.25%	50 Min	1-1.5 Hours	8-10 Hours	12 Hours	6 Days
66-75°F (19-23°C)	0.20%	40 Min	45-60 Min	7-8 Hours	9-10 Hours	6 Days
76-85°F (24-29°C)	0.10%	40 Min	45-60 Min	7-8 Hours	9-10 Hours	6 Days
86-100°F (30-38°C)	N/A	30 Min	45-60 Min	6-7 Hours	7-8 Hours	6 Days

* Do not use PS40 accelerator in temperatures over 85°F (29°C)

Only mix enough material to be applied on initial coat. Always add component B activator to component A paint. Complete kit of material will yield 2 US Gallons (7.5 liters). 1-gallon component A paint, 1-gallon component B activator.

Apply one even wet coat of material using a uniform spray pattern. Cross coat may be used to achieve 100% coverage in one single coat depending on color. Note: Apply only one coat of material to achieve proper gloss requirement of product.

Glair G30 Series

Semi-Gloss & Flat Colors

High Solid Polyurethane Topcoat



Application Instructions PS40 Accelerator (Fast dry additive mix options for touch up applications)

PS40 Accelerator	Dry Between Coats	Dry to Handle	Dry Hard	Pot Life	Full Cure
0.25% By Volume	12 Minutes	2 Hours	4 Hours	4 Hours	6 Days
0.30% By Volume	10 Minutes	1.5 Hours	3 Hours	3 Hours	6 Days
0.40% By Volume	5 Minutes	45 Minutes	1 Hour	45 Minutes	6 Days

*Note: Overuse of PS40 additive may affect product gloss and finish

Force Cure: If deemed necessary oven curing is possible to reduce dry to tape and handle times. After application, allow coating to air dry for 1 hour at room temperature (75° F), then force cure for 2 hours at 120° F.

Theoretical Coverage 800-900 sq. ft / gallon @ 1 mil 20-22m² / liter @1 mil
*Coverage based on 100% transfer efficiency rate

Color Available in all color ranges

Gloss Semi-Gloss colors: 17-30 @ 60 degrees
Flat/Matt Colors: Less than 5 @ 60 degrees
*Also available is custom gloss ranges

Volatile Organic Compound 340 – 390 g/l

Shelf Life 24 Months (When stored in climate-controlled environment between 60-80° F)
*Product may be re-certified upon inspection by 3Chem.

Safety Instructions Always read material safety data sheet (SDS) and product label before utilizing this product. Product SDS is available upon request.

3Chem Corporation Disclaimer

All information, recommendations, statements, and technical data contained herein are not intended to be comprehensive or exhaustive, but instead are based on tests utilizing present knowledge and current laws. The accuracy and completeness of said tests are in no way guaranteed, nor should they be construed as an express or implied warranty. We believe such information, recommendations, statements, and technical data to be reliable and accurate, but we have no control over the quality or the condition of the many factors affecting the use and application of the product. The user shall depend upon its/his/her own information, data and testing to determine whether the product is suitable for the user's intended use and the user assumes all risks and liability resulting from its/his/her use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. All products supplied, and technical advice given is subject to our standard terms and conditions of sale. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

*Brand names mentioned above are either trademarks of or licensed to 3Chem Corporation.