

SOCOGLAZE-85285

High Solid Polyurethane Topcoat



Product SOCOCGLAZE 85285

Item Class High Solid Polyurethane Topcoat

SOCOGLAZE 85285 Series is a high solid polyurethane topcoat formulated to provide superior resistance and excellent coverage for military and defense applications. With an average 50% solid per gallon; it also offers better coverage than most other polyurethane coatings on the market. This product is formulated to surpass conventional polyurethanes with superior chemical resistance and flexibility.

Specifications This product is qualified to the following specifications:

Gloss Colors: MIL-PRF-85285F Ty I & II, Cl H, Form M, Gr N

Gloss Colors: MIL-PRF-85285F Ty IV, Cl H, Form M, Gr P

Semi-Gloss and Flat Colors: MIL-PRF-85285F Ty I, II, IV, Cl H, Form M, Gr N

Catalyst & Additives **Catalysts/Activators** **Additives (Optional)**

361 - Gloss White	PS40 Accelerator
362 - Semi-Gloss & Flat Colors	HF12 High Humidity Additive
363 - Gloss Non-White Gloss Colors	CS28 Slow Thinner Reducer
	CM100 Medium Thinner Reducer
	CF3 Fast Thinner Reducer

Use of Primers 3Chem recommends using SOCOCGLAZE 23377-1-YC2 (High Solid Epoxy Primer) with this system. Please contact your local 3Chem representative for a complete list of epoxy primers which may be utilized with this system.

Surface Preparation Prepare substrate per OEM requirements. Refer to Glair application guide for detailed instructions or contact your local 3Chem representative for assistance.

Mixing Instructions

Base	Catalyst/Activator	Mix Ratio
SOCOGLAZE 85285 Gloss White Colors	361	3:1
SOCOGLAZE 85285 Semi-Gloss & Flat Colors	362	3:1
SOCOGLAZE 85285 Gloss Non-White Colors	363	3:1

Shake (Base) for 15 minutes to assure no solid settlement remains in can. Add component B catalyst to component A paint first. Mix ratio for material is 3-parts component A paint, 1-part component B catalyst. Kit yields 1 gallon. Product viscosity is contingent on environmental conditions.

Induction Time Although no induction time is needed. Once mixed together, ensure that admixed material is continuously stirred for at least 5 minutes before proceeding.

Spraying Viscosity 17-24 Seconds with #2 Zahn cup (Once thinner is added)

SOCOGLAZE-85285

High Solid Polyurethane Topcoat



Pot Life 7 Hours @ 21° Celsius, 70° Fahrenheit (Higher temperatures will shorten pot life)

Film Thickness 2-3 Mils DFT (2 Coats @ 1-1.5 DFT) Wet film thickness should be 4-6 Mils total between 2 coats

Application Instructions

Temperature and Humidity	Minimum	Maximum
Temperature Celsius	11°	35°
Temperature Fahrenheit	52°	95°
Humidity	33%	74%

**For Humidity above 74%, use HF12 Additive. Max recommended relative humidity at application is 90%. HF12 high humidity additive should be added to admix material (paint, activator, thinner) at a rate of 2% max by volume.

Spray Equipment

Spray Gun Type	Tip/Nozzle Size	Air Pressure	Pot Pressure
Conventional Air	1.3 - 1.6 mm	40 to 60 psi	10 to 20 psi
HVLP	1.4 - 1.6mm	10 psi at cap	10 to 20 psi
Air Electrostatic	1.2 - 1.5mm	45 to 60 psi	10 to 40 psi
Air Assist Airless Electrostatic	.23 - .34 mm	40 to 60 psi	700 to 1200 psi

Temperature	Wet-Edge	Time Between Coats	Dry to Tape	Dry to Handle	Full Cure
52-65°F (11-18°C)	40 Min	1-1.5 Hours	7-8 Hours	10 Hours	7 Days
66-93°F (19-34°C)	35 Min	45-60 Min	6-7 Hours	8-9 Hours	7 Days
94-100°F (35-38°C)	30 Min	30-40 Min	5-7 Hours	7-8 Hours	7 Days

Only mix enough material to be applied on initial coat. Always add component B catalyst to component A paint. Complete kit of material will yield 1 US Gallons (3.75 liters). 3/4-gallon component A paint, 1-quart component B catalyst.

Always check product viscosity using #2 Zahn cup to confirm viscosity. If needed, admixed material may be thinned up to 10% by volume with a 3Chem recommended thinner based on environmental conditions.

Shake (Base) for 15 minutes to assure no solid settlement remains in can. Add component B catalyst to component A paint first. Then add recommended thinner from chart below. Use of optional thinner depends on environmental conditions. Mix ratio for material is 3-parts component A paint, 1-part component B catalyst and 10% (max) parts thinner (Optional). Additives such as PS40 dry time accelerator may also be used but are not required. See chart below for use of this additive.

Gloss Colors:

Apply one tack coat of material using a uniform spray pattern. Wait recommend time between coats based on chart above. The initial coat should be tacky before applying a second coat. Applying the second coat too early will lead to possible running of material. Waiting too long will lead to a dull finish. Mix enough material to be applied on the second coat. Use the same mixing instruction from the initial coat above.

Apply a second medium wet coat using a uniform spray pattern. The second coat must appear wet and uniform once complete. Take care not to leave any dry areas or spots. Wet these areas if necessary, to ensure a uniform finish. Wait appropriate dry to tape or dry to handle time based on chart above.

SOCOGLAZE-85285

High Solid Polyurethane Topcoat



Semi-Gloss and Flat Colors:

Apply one even wet coat of material using a uniform spray pattern. Cross-coats may be used to achieve 100% coverage in one single coat depending on color. Note: Apply only one coat of material to achieve proper gloss requirement for the product.

Application Instructions

PS40 Accelerator (Fast dry additive mix options)

PS40 Accelerator	Dry Between Coats	Dry to Handle	Dry Hard	Pot Life	Full Cure
0.25% By Volume	12 Minutes	2 Hours	4 Hours	4 Hours	6 Days
0.30% By Volume	10 Minutes	1.5 Hours	3 Hours	3 Hours	6 Days
0.40% By Volume	5 Minutes	45 Minutes	1 Hour	45 Minutes	6 Days

*Note: Overuse of PS40 additive may affect product gloss and finish

Force Cure: If deemed necessary oven curing is possible to reduce dry to tape and handle times. After application, allow coating to air dry for 30 minutes at room temperature (75° F), then force cure for 1 hour at 120° F.

Theoretical Coverage

800-900 sq. ft / gallon @ 1 mil 20-22m2 / liter @1 mil

*Coverage based on 100% transfer efficiency rate

Dry Film Weight

Per 25 microns: 27-35 g/m2

Per dry mil: .0057-.0082 lbs./ft2

Color

Available in all color ranges including AMS-STD-595, BAC, RAL, etc.

Gloss

Gloss colors: >90 GU @ 60 degrees

Semi-Gloss Colors: 17-24 GU @ 60 degrees

Flat Colors: <5 @ 60 degrees

Volatile Organic Compound

220-340 g/l (Use of thinner will increase product V.O.C)

Shelf Life

24 Months (When stored in climate-controlled environment between 60-80° F)

*Unopened product may be re-certified upon inspection by 3Chem.

Safety Instructions

Always read material safety data sheet (SDS) and product label before utilizing this product. Product SDS is available upon request.

3Chem Corporation Disclaimer

All information, recommendations, statements, and technical data contained herein are not intended to be comprehensive or exhaustive, but instead are based on tests utilizing present knowledge and current laws. The accuracy and completeness of said tests are in no way guaranteed, nor should they be construed as an express or implied warranty. We believe such information, recommendations, statements, and technical data to be reliable and accurate, but we have no control over the quality or the condition of the many factors affecting the use and application of the product. The user shall depend upon its/his/her own information, data and testing to determine whether the product is suitable for the user's intended use and the user assumes all risks and liability resulting from its/his/her use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. All products supplied, and technical advice given is subject to our standard terms and conditions of sale. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

*Brand names mentioned above are either trademarks of or licensed to 3Chem Corporation.