

FlyGloss FGCC Clear Coat

Acrylic Polyurethane Topcoat



Product FlyGloss FGCC Clear Coat

Item Class Base Coat / Clear Coat System

FlyGloss FGCC acrylic polyurethane clear coat is intended to be applied over FGBC base coat to achieve superior gloss and color retention that outshines and outlasts preceding aerospace market technologies. FGCC clear coat offers a gloss of 95+. It has excellent wetting properties and is buffable for up to 72 hours. This product is also resistant to various aerospace chemicals and solvents including hydraulic fluid.

Specifications Product is manufactured to meet the performance requirements of the following specifications:

AMS 3095B* - AIMS 04-04-025 - AIMS 04-04-033 - AIMS 04-04-037 - BAMS 565-018 - MEP 10-125 Type I* - BAMS 565-018 (*Listed on QPL)

Activator & Additives	Activator	Thinner	Repair Accelerator
	900	FG4001 Normal Conditions FG4002 Higher Temperatures FG4003 Colder Temperatures	PS50

Use of Primers 3Chem recommends use of P1019 (High Solid Epoxy Primer) and P-1069 (Surfacing Primer) with this system. Please contact your local 3Chem representative for a complete list of epoxy primers which may be utilized with this system.

Surface Preparation Prepare substrate per OEM requirements. Refer to Glair application guide for detailed instructions or contact your local 3Chem representative for assistance.

Base	Finish	Activator	Mix Ratio	Optional Thinner
FGCC-XXXX	Required Clear Coat	900	1:1	2-5% Max (By Volume)

Lightly stir (Base) for 3-5 minutes. Add component B activator to component A paint first. Mix ratio of material is 1-part component A paint, 1-part component B activator. Optional thinner may be used, recommended thinner amount is 2-5% by volume. Do not exceed 5% reduction. *** FGCC must be used in conjunction with FlyGloss FGBC base coat to meet specification requirements.

Induction Time No induction time is necessary for this product. Once mixed, ensure that admixed material is continuously stirred for at least 5 minutes before proceeding.

Spraying Viscosity 16-20 Seconds with #2 Zahn cup

FlyGloss FGCC Clear Coat

Acrylic Polyurethane Topcoat



Pot Life 8 Hours @ 21° Celsius, 70° Fahrenheit

Film Thickness .75-1.25 mils DFT (Only one coat required) Wet film thickness should be 1.5-2 mils total

Application Instructions

Temperature and Humidity	Minimum	Maximum
Temperature Celsius	11°	35°
Temperature Fahrenheit	52°	95°
Humidity	33%	74%

Spray Equipment

Spray Gun Type	Tip/Nozzle Size	Cap Pressure	Pot Pressure
Conventional Air	1.3 - 1.6 mm	45 to 60 psi	10 to 20 psi
HVLP	1.4 - 1.6mm	10 psi Maximum	10 to 20 psi
Electrostatic	1.2 - 1.5mm	45 to 60 psi	10 to 40 psi

Dry Times

Temperature	Wet-Edge	Touch Dry	Dry to Handle	Full Cure
52-65°F (11-18°C)	2 Hours	12 Hours	16 Hours	7 Days
66-85°F (19-29°C)	1 Hour	8 Hours	12 Hours	7 Days
86-95°F (30-35°C)	45 Min	7 Hours	10 Hours	7 Days

Oven Force Dry Instructions 1:1

Flash Time	Oven temperature	Dry to Handle	Full Cure
1 Hour	2 hour @ 120° F (43°C)	3 Hours	7 Days

Ensure that FlyGloss base coat surface is clean from any contaminants. Use industry approved tack cloth on all surfaces immediately prior to FlyGloss FGCC clear coat application.

Only mix enough material to be applied on the initial coat. Always add component B activator to component A paint. Complete kit of material will yield 2 US Gallons (7.57 liters). 1-gallon component A paint, 1-gallon component B activator, Max optional thinner amount is 12.8 oz/ 378 ml (5% by Volume).

Apply one even wet coat of material using a uniform spray pattern. Second coat may be applied if desired.

Application Instructions PS50 Accelerator (Repair Application)

PS50 Required	Pot Life	Dry to Handle	Full Cure
1oz/29ml per admixed gallon	30 Minutes	2.5 Hours	7 Days

Theoretical Coverage 900-1000 sq. ft / gallon @ 1 mil 21-23 m² / liter @1 mil
*Coverage based on 100% transfer efficiency rate

FlyGloss FGCC Clear Coat

Acrylic Polyurethane Topcoat



Dry Film Weight

Per 25 microns: 1.15 g/m²
Per dry mil: .0057 lbs./ft²

Color

Clear / Transparent

Gloss

95 minimum @ 60 degrees

Volatile Organic Compound 380 g/l

Shelf Life

24 Months (When stored in climate-controlled environment between 60-80° F)
*Product may be re-certified upon inspection by 3Chem.

Safety Instructions

Always read material safety data sheet (SDS) and product label before utilizing this product. Product SDS is available upon request.

3Chem Corporation Disclaimer

All information, recommendations, statements, and technical data contained herein are not intended to be comprehensive or exhaustive, but instead are based on tests utilizing present knowledge and current laws. The accuracy and completeness of said tests are in no way guaranteed, nor should they be construed as an express or implied warranty. We believe such information, recommendations, statements, and technical data to be reliable and accurate, but we have no control over the quality or the condition of the many factors affecting the use and application of the product. The user shall depend upon its/his/her own information, data and testing to determine whether the product is suitable for the user's intended use and the user assumes all risks and liability resulting from its/his/her use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. All products supplied, and technical advice given is subject to our standard terms and conditions of sale. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

*Brand names mentioned above are either trademarks of or licensed to 3Chem Corporation.